

CASQUILLOS


Casquillo Liso C

Material: 1,7264

Tratamiento: Carbonitrurado prof. 0,6

Dureza: 60-62 HRC

Forma de pedido: C/di x li x L



d1	d2	L							
		9	17	21	26	30	35	45	55
10	14	•	•						
12	16		•		•				
14	20			•		•			
16	20			•		•			
18	25			•		•			
20	30					•			
22	30						•	•	
25	35						•	•	
30	40						•	•	
40	50								•


Casquillo Valona CV

Material: 1,7264

Tratamiento: Carbonitrurado prof. 0,6

Dureza: 60-62 HRC

Forma de pedido: CV/di x li x L



d1	d2	D	a	L										
				17	21	26	35	45	55	65	75	85	95	115
10	14	17	4	•		•								
12	16	20	4	•		•	•	•	•					
14	20	24	4		•	•	•	•						
16	20	24	4		•	•	•	•			•			
18	25	30	6		•	•	•	•	•	•	•	•	•	
20	30	35	6			•	•	•	•	•	•	•	•	
22	30	35	6			•	•	•	•	•	•	•	•	
25	35	40	8				•	•	•		•			
30	40	45	8			•	•	•	•	•	•	•	•	•
40	50	54	10						•			•	•	