

COMPLEMENTOS

AXSON EPO 999

Resina colable para la construcción de moldes.

Contenido resina: 1 x 1,500 g.

Contenido endurecedor: 1 x 0,090 g.

AXSON EPO 999

Surface and mas casting compound

Contents resin: 1 x 1,500 g.

Contents hardener: 1 x 0,090 g.



PROPIEDADES FÍSICAS PROCESSING DATA AND PHYSICAL PROPERTIES

Proporción <i>Mixing ratio resin hardener</i>	Peso <i>by weight</i>	100	100
Term de proceso <i>Processing temperature</i>	°C	18	22
Vida útil <i>Pot life 20°C (500 g specimen)</i>	min.	8-10	
Desmoldeable <i>Desmoulding time at R.T.</i>	h	2-3	
Tiempo de secado <i>hardening time</i>	h	5	
Color <i>Colour</i>		azul <i>blue</i>	
Dureza <i>hardness</i>	Shore D	75-80	
Compresión <i>Compressive strength</i>	N/mm ²	65	
Dilatación lineal <i>Linear shrinkage (test specimen 1000 x 40 x 40 mm)</i>	96	0.016-0,2	