

COMPLEMENTOS

RZ-20

Resina colable Rezolín para la construcción de modelos.

Contenido resina: 1 x 0,500 g.

Contenido endurecedor: 1 x 0,050 g.

RZ-20

Surface and mas casting compound

Contents resin: 1 x 0,500 g.

Contents hardener: 1 x 0,050 g.



PROPIEDADES FÍSICAS PROCESSING DATA AND PHYSICAL PROPERTIES

Proporción <i>Mixing ratio resin hardener</i>	Peso <i>by weight</i>	100	10
Term de proceso <i>Processing temperature</i>	°C	18	22
Vida útil <i>Pot life 20°C (500 g specimen)</i>	min.	45	60
Desmoldeable <i>Desmoulding time at R.T.</i>	h		16
Tiempo de secado <i>hardening time</i>	h		24
Color <i>Colour</i>			negro <i>pale black</i>
Dureza <i>hardness</i>	Shore D		90
Compresión <i>Compressive strength</i>	N/mm ²		110
Dilatación lineal <i>Linear shrinkage (test specimen 1000 x 40 x 40 mm)</i>		96	0.016
Peso específico	•		1.75